

# **Product Specifications**

Prismatic LFP Battery Cell

Model: IFPP100

## Contents

| 1. Ierms and definitions                           | 3  |
|--|----|
| 2. Scope of application                            | 4  |
| 3. Product Type                                    | 4  |
| 4. Basic performance                               | 4  |
| 5. Charging performance                            | 5  |
| 6. Discharge performance                           | 5  |
| 7. Cycle life                                      | 6  |
| 8. Storage performance                             | 6  |
| 9. Safety performance                              | 6  |
| 10. Marking, packaging, transportation and storage | 7  |
| 11. Prohibitions and precautions                   | 8  |
| Attached :Dimensions of single battery             | 10 |

### 1. Terms and definitions

### 1.1. Products:

The "product" in this specification refers to IFPP100 rechargeable lithium iron phosphate battery produced by Chunlan.

### **1.2.** Room temperature:

25±2 °C .

### **1.3.** Battery temperature:

The temperature of the positive pole of the battery.

### 1.4. Rated capacity:

Nominal capacity, expressed by C<sub>rated</sub>

### **1.5.** Initial capacity:

The capacity ( Ah ) of a new battery discharged from the factory when it is fully charged at room temperature and discharged to the specified discharge termination condition with a discharge current of  $I_1$  is expressed by C  $_0$ .

The I<sub>1</sub>: 1 hour rate discharging current (A), which value is equal to C<sub>rated</sub> (A).

#### **1.6.** Actual capacity:

The value of the capacity released from a fully charged battery cell under specified conditions.

### 1.7. Working voltage:

Working voltage, also known as discharge voltage or load voltage, refers to the potential difference between the cell positive and negative terminals when the load current is flowing.

### **1.8.** Capacity retention rate:

After a fully charged battery has been stored at a certain temperature for a period of time, the ratio of the discharge capacity of the battery to the initial capacity under the specified discharge conditions.

### **1.9.** Capacity recovery rate:

After a fully charged battery has been stored for a period of time at a certain temperature, it is fully charged and then discharged.

The ratio to the initial capacity.

### **1.10.** State of charge:

The percentage of the actual capacity that can be released by the current battery cell according to the specified discharge conditions. Referred to as SOC .

### **1.11.** Cycle life:

Under the specified charge-discharge termination conditions, charge and discharge with a specific charge-discharge system, the actual capacity of the battery is greater than the number of cycles that can be performed before 80% of the initial capacity.

### 2. Scope of application

Electric vehicle/energy storage/UPS

### 3. Product Type

### 3.1. Product classification:

Rechargeable prismatic lithium iron phosphate battery

#### **3.2.** Product model:

IFPP100

### 4. Basic performance

|   | 1  |                  |   |
|---|--|------------------|---|
| project   | specification  | condition        | Remarks                                   |
| Appearance                                      | No cracks,<br>scratches,<br>deformation,<br>stains, electrolyte<br>leakage, etc. |                  |   |
| Nominal size<br>(Thickness ×<br>width × height) | 36× 130× 230   |                  | See<br>attached<br>picture for<br>details |
| Nominal Weight                                  | 2.30±0.05kg  |                  |   |
| Rated Capacity                                  | 100Ah  |                  |   |
| Nominal Voltage                                 | 3.2V   |                  |   |
| Operating voltage range                         | 2.5V-3.65V   | Room temperature |   |

| AC internal    | ≤ 0.60m Ω    | SOC40% , AC 1kHz , room |  |
|----------------|--------------|-------------------------|--|
| resistance     | 2 0.00111 12 | temperature             |  |
| DC internal    | ≤ 1.00m Ω    | SOC50% , 400A,10S, room |  |
| resistance     | ≥ 1.00111 12 | temperature             |  |
| Energy Density | ≥135Wh/kg    |                         |  |

## **5.** Charging performance

| project                            | specification     | condition  | Remarks                           |
|------------------------------------|-------------------|--|-----------------------------------|
| Standard<br>charging               | 1/2I <sub>1</sub> | Room temperature,<br>constant current to constant<br>voltage, cut-off current 0.05I<br>1, cut-off voltage<br>3.65V | Recommended<br>charging<br>method |
| Data shaqrin s                     | Sustainable 120A  | Room temperature, SOC ≤80%   |                                   |
| Rate charging                      | Pulseable300A,10S | Room temperature, SOC ≤80%   |                                   |
| Charging cut-off voltage           | 3.65V             | 25±2℃, ≤1 l <sub>1</sub>   |                                   |
| Highest<br>temperature<br>charging | 65 ℃              |  |                                   |

## **6.** Discharge performance

| project                             | specification             | condition   | Remarks |
|-------------------------------------|---------------------------|---|---------|
| Standard discharge capacity         | ≥ 100% C <sub>Rated</sub> | Room temperature, 1I <sub>1</sub> , cut-off voltage 2.5V    |         |
| Rate discharge                      | Sustainable 400A          | Room temperature  |         |
| nate discharge                      | Pulseable500A,30S         | Room temperature  |         |
| Low temperature discharge capacity  | ≥70%C <sub>0</sub>        | -20 $^{\circ}\mathrm{C}$ , 1I $_{1}$ , cut-off voltage 2.0V |         |
|                                     | ≥80%C <sub>0</sub>        | -10 $^{\circ}$ C, 1I <sub>1</sub> , cut-off voltage 2.0V    |         |
| High temperature discharge capacity | ≥98%C <sub>0</sub>        | 45 $^{\circ}$ C , 1I $_{1}$ , cut-off voltage 2.5V          |         |

|  | ≥95%C <sub>0</sub> | 55 $^{\circ}$ C , 1I $_{1}$ , cut-off voltage 2.5V |  |
|--|--------------------|--|--|
|--|--------------------|--|--|

## **7.** Cycle life

| project             | specification | condition   | Remarks |
|---------------------|---------------|---|---------|
| Standard cycle life | ≥ 3000 times  | Room temperature, 0.5I <sub>1</sub> charge, 1I <sub>1</sub> discharge |         |

## 8. Storage performance

| project                             | specification | condition   | Remarks |
|-------------------------------------|---------------|---|---------|
| Room<br>temperature                 |               | Room temperature, 28  |         |
| capacity retention                  | ≥ 95%         | days  |         |
| rate                                |               |   |         |
| High temperature capacity retention | ≥ 95%         | 55 °C , 7 days  |         |
| rate                                |               |   |         |
| Room                                |               |   |         |
| temperature                         | ≥ 97%         | Room temperature, 28  |         |
| capacity recovery                   | 2 3770        | days  |         |
| rate                                |               |   |         |
| High temperature                    |               |   |         |
| capacity recovery                   | ≥ 96%         | 55 $^{\circ}\!$ |         |
| rate                                |               |   |         |

## **9.** Safety performance

| project                | specification                      | condition                | Remarks |
|------------------------|------------------------------------|--------------------------|---------|
| Overdischarge          | No fire, no explosion, not leakage | Refer to GB/T 31485-2015 |         |
| Overcharge             | No fire, no explosion              | Refer to GB/T 31485-2015 |         |
| External short circuit | No fire, no explosion              | Refer to GB/T 31485-2015 |         |
| fall                   | No fire, no explosion, not leakage | Refer to GB/T 31485-2015 |         |

| project              | specification                      | condition                | Remarks |
|----------------------|------------------------------------|--------------------------|---------|
| heating              | No fire, no explosion              | Refer to GB/T 31485-2015 |         |
| extrusion            | No fire, no explosion              | Refer to GB/T 31485-2015 |         |
| Sea water immersion  | No fire, no explosion              | Refer to GB/T 31485-2015 |         |
| Temperature<br>cycle | No fire, no explosion, not leakage | Refer to GB/T 31485-2015 |         |
| Low pressure         | No fire, no explosion, not leakage | Refer to GB/T 31485-2015 |         |

### 10. Marking, packaging, transportation and storage

### **10.1.** Logo

There should be a clear barcode on each product.

### 10.2. Packaging

The product should have outer packaging to ensure that the product is not mechanically damaged during transportation, loading, unloading, and stacking.

### **10.3.** Transportation

- 10.3.1. Batteries should be packed into boxes for transportation under <60% charged state.

  During transportation, violent loading and unloading should be strictly prohibited,
  severe vibration, impact or squeezing, protection from sun and rain, and no side or
  upside-down.
- 10.3.2. Suitable for transportation of vehicles, trains, ships and other means of transportation.
- 10.3.3. Please refer to MH/T 1020-2018 "Regulations for Air Transport of Lithium Batteries " for air transportation.

### **10.4.** Storage

10.4.1. Products without opening the package should be stored in a clean, dry and ventilated warehouse with an ambient temperature of -10  $^{\circ}$ C  $^{\circ}$ 35  $^{\circ}$ C and a relative humidity of  $\leq$  75 %. The warehouse should not contain corrosive gas; the product should be kept away from fire Source and heat source;

- 10.4.2. During storage, it is forbidden to turn the battery upside down, and avoid mechanical shock and heavy pressure.
- 10.4.3. The state of charge should be stored at 40% SOC . When the battery is not used for a long time, the battery shall be charged and discharged as a standard maintenance every six months, and the battery shall be stored under 20%-40% charged state.

### 11. Prohibitions and precautions

- ★ use, you should read the specifications in detail and fully understand the contents of the cautions and prohibitions.
- ★ have been professionally trained and qualified should contact, use and maintain the battery, and take adequate protective measures. Improper use may cause battery performance degradation, failure, or fire or explosion, resulting in personal or property damage.

#### 11.1. Prohibited matters

- ★ not overheat the battery.
- \* strictly prohibited to modify or disassemble the battery.
- ★ strictly forbidden to pierce the battery with a sharp object.
- ★ strictly forbidden to drop, hit or bend the battery.
- ★ strictly forbidden to connect the positive and negative poles of the battery directly.
- ★ strictly forbidden to weld the battery pole directly.
- ★ strictly prohibited to mix with other batteries.
- ★ strictly prohibited to use the positive and negative poles upside down.
- ★ reverse charging is strictly prohibited.
- ★ over-discharge is strictly prohibited.
- ★ strictly forbidden to turn the battery upside down.
- ★ strictly forbidden to put the battery in water or other conductive liquids, or cause condensation on the surface of the battery.
- \* strictly forbidden to connect the negative pole to the battery case.

#### **11.2.** Notes

### 11.2.1. Notes on charging

- ★ charging current shall not exceed the maximum allowable charging current specified in this specification.
- ★ charging voltage must not exceed the maximum charging voltage specified in this specification.
- ★ battery must be charged within the range of 0  $^{\circ}$ C  $^{\circ}$ 65 $^{\circ}$ C , and the best charging temperature is 15-35  $^{\circ}$ C .

### 11.2.2. Discharge precautions

- ★ discharge current must not exceed the maximum discharge current specified in this specification.
- ★ battery must be discharged within the range of -20  $^{\circ}$ C  $^{\circ}$ C . The best discharge temperature is recommended to be 15-35  $^{\circ}$ C .
- ★ matter what discharge mode the battery is in, once the battery temperature exceeds the maximum discharge temperature, the discharge will stop.
- ★ battery should be charged regularly to keep the battery at 20%~40% charged state to prevent over-discharge.

### **11.3.** Other matters

- ★ any matters not mentioned in this specification, please consult our company. When the version of this specification is updated, our company will not give further notice.
- ★ company does not assume any responsibility for accidents caused by using the battery cell outside the conditions stated in this document.
- ★ company does not assume any responsibility for problems caused by improper use of single cells with circuits, battery packs, and chargers.
- ★ assembly process of battery cells after shipment, the defective battery cells caused by processing are not included in the scope of quality assurance.

Attached :Dimensions of single battery cell



